

## Product Description

Anabond 112 is a single component dimethacrylate ester based fast curing high strength anaerobic adhesive system specially designed for permanent locking of threaded fasteners. The product gets polymerized when confined between closely mating metal surfaces in the absence of air and prevents loosening and leakage from shock and vibration. The product exhibits good temperature performance, chemical resistance and lubricating property.

The product is suited for heavy duty applications and typical applications include locking of large bolts and studs under M20 such as studs into motor housings, nuts onto studs in pump housings and other fasteners where high strength is required.

|                |                                  |
|----------------|----------------------------------|
| Chemical Type  | : <b>Dimethacrylate ester</b>    |
| Appearance     | : <b>Medium viscous liquid</b>   |
| Cure initiator | : <b>Anaerobic</b>               |
| Application    | : <b>Thread locking adhesive</b> |
| Strength       | : <b>High</b>                    |
| Colour         | : <b>Red</b>                     |

## Properties of uncured material

|   |            |
|---|------------|
| Specific Gravity at 30 °C,<br>ATM - R004 x (JIS K6820)                  | 1.0 - 1.1  |
| Viscosity at 30 °C, Brookfield DV-II+,<br>Spindle 2, speed 100 rpm, cP, | 275 - 325  |
| Flash point   | refer MSDS |

## Curing performance

The product cures when confined in the absence of air between close fitting metal surfaces. The curing time is influenced by the gap between the surfaces, the kind of metal, surface treatments and temperature. The assembly can be subjected to limited test after functional cure. Although functional cure is developed in relatively short time, curing continues for at least 24 hours before full properties are developed. Curing tested according to ATM\* - R031 (ISO 10964).

|                                      |         |
|--------------------------------------|---------|
| Handling cure at 30 ± 2 °C, minutes  |         |
| M10 steel bolts & Nuts               | 05 - 15 |
| M10 Chrome plated steel bolts & Nuts | 15 - 25 |
| Functional cure at 30 ± 2 °C, h      | 6       |
| Full cure at 30 ± 2 °C, h            | 24      |

## Operating Parameters

|                     |    |              |
|---------------------|----|--------------|
| Recommended gap     | mm | 0.15         |
| Service temperature | °C | -50 to + 150 |

## Properties of cured material

Cured for 24 hours at 30 ± 2 °C, tested according to ATM - R031 (ISO 10964).

|  |                |                        |
|--|----------------|------------------------|
| Breakaway torque,<br>M10 steel bolts and nuts  | N.m<br>(kgf.m) | 28 - 40<br>(2.8 - 4.0) |
| Prevailing torque,<br>M10 steel bolts and nuts | N.m<br>(kgf.m) | 29 - 40<br>(2.9 - 4.0) |

## Typical Environmental Resistance

Cured for 24 hours at 30 ± 2 °C, Breakaway torque tested on M10 steel Bolts and nuts according to ATM - R031 (ISO 10964).

## Chemical resistance

Aged under conditions indicated and tested at 30 ± 2 °C.

| Chemicals                      | % of initial strength |      |       |
|--------------------------------|-----------------------|------|-------|
|                                | 100h                  | 500h | 1000h |
| Motor oil 10W30,125 °C         | 100                   | 99   | 99    |
| Motor oil 20W40,125 °C         | 100                   | 99   | 98    |
| Gasoline, 25 °C                | 100                   | 95   | 86    |
| Water / Glycol, 50 / 50, 87 °C | 96                    | 84   | 80    |

## General information

Before handling read product safety data sheet and container label for safe use.

This product is not recommended for use in pure oxygen or oxygen rich systems and not be selected as a sealant for chlorine or other strong oxidizing materials.

To prevent the product from clogging in the nozzle, do not allow the tip to touch the metal surfaces during application.

Do not return the used product back to the original container as it may be contaminated during usage.

Where aqueous washing systems are used to clean the surfaces before bonding, it is important to check the compatibility of the washing solution with the adhesive. In some cases these aqueous washes can affect the cure performance of the adhesive.

The product is not normally recommended for use on plastics, particularly thermoplastic materials where stress cracking of plastic could result. Users are recommended to check the compatibility of the product with such substrates.

## Direction for use Substrate preparation

- All surfaces must be clean and dry.
- For best results degrease the fasteners with suitable solvent and allow it to dry before applying the adhesive.
- If the metal surface is inactive or curing speed is slow use activator, Anabond Ekaprime 021.

## Method of application

- Shake the product thoroughly before use.
- Apply required drops of the product on the mating area of the bolt and nut. Rotate the bolt or nut for uniform coverage and then tighten as required. Parts should not be disturbed until sufficient handling strength is achieved.
- For through holes, apply several drops of the product on to the bolt at the nut engagement area.
- For blind holes, apply several drops of the product down the internal threads to the bottom of the hole.

## Disassembly and cleaning

- Remove with standard hand tools.
- When hand tools do not work, heat the assembly to approximately 250 °C and disassemble while hot.
- Cured product can be removed with a combination of soaking in a solvent and mechanical abrasion such as a wire brush.

## Storage

- Store the material in its original container in a cool and dry condition between 8 and 35 °C. Keep away from heat source and direct sunlight.
- Storage other than recommended temperature and conditions will have impact on the properties of the product.
- The product is non-volatile and non-flammable at room temperature.

| SKU                                  | Packaging      |
|--------------------------------------|----------------|
| 50ml , 250ml ,500 ml , 3.5 ml & 54 g | HDPE container |

## Shelf life

Fifteen months from the date of manufacture in it's original container, unopened and recommended storage conditions.

## Unit Conversion

|   |   |
|---|---|
| $(^{\circ}\text{C} \times 1.8) + 32 = ^{\circ}\text{F}$ | $\text{N} \times 0.225 = \text{lb}$               |
| $\text{kgf.m} \times 9.81 = \text{N.m}$                 | $\text{N.m} \times 8.851 = \text{lb.in}$          |
| $\text{MPa} \times 145 = \text{psi}$                    | $\text{N} / \text{mm} \times 5.71 = \text{lb/in}$ |
| $\text{mPa.s} = \text{cP}$                              | $\text{N.m} \times 0.738 = \text{lb.ft}$          |
| $\text{mm} / 25.4 = \text{inches}$                      | $\text{N.m} \times 0.142 = \text{oz.in}$          |
| $\mu\text{m} / 25.4 = \text{mil}$                       |   |



# Anabond<sup>®</sup>

# Technical Data Sheet

Technology : Dimethacrylate ester

Product name : Anabond 112

Revised date : March 2018

Revision No. : 01

## Disclaimer - Please read carefully

- The data contained herein are furnished for information only and are believed to be reliable. We cannot assume responsibility for the results obtained by others over whose methods we have no control.
- It is the user's responsibility to determine suitability for the user's purpose of any production methods mentioned herein and to adopt such precautions as may be advisable for the protection of property and of persons against any hazards that may be involved in the handling and use thereof.
- In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered.
- Anabond disclaims liability for any incidental or consequential damages of any kind, including lost profits.

### For product information, contact :

**Anabond Limited**

No.36, Type II, Dr. V.S.I Estate,  
Thiruvanmiyur, Chennai, TN - 600041.

**Ph** : +91 (44) 23460041/42/43

**Fax** : +91 (44) 2346 0048

**e-mail** : [marketing@anabond.com](mailto:marketing@anabond.com)

**web** : [www.anabond.com](http://www.anabond.com)